

# 38% Sodium Aluminate

38% Sodium Aluminate

Product Bulletin

100% of raw material base is purchased from primary producers as virgin material.

9213 Arch Street Pike  
 Little Rock, AR 72206  
 USA  
 Tel: +1 501 888 1211  
 Toll Free 800 453 2586

Please send email enquiries to:  
[wtc.sales@geosc.com](mailto:wtc.sales@geosc.com)

Website: [www.geosc.com](http://www.geosc.com)

Property	Minimum	Target	Maximum
Al <sub>2</sub> O <sub>3</sub> , (%)	19.6	20.0	20.40
Na <sub>2</sub> O, (%)	18.0	18.5	19.0
Iron (ppm Fe)	X	X	20.00
Density (lb/gal)	11.67	12.09	12.51
Specific Gravity	1.400	1.450	1.500
Silica	X	20.00	X
Molar Ratio (Na <sub>2</sub> O:Al <sub>2</sub> O <sub>3</sub> )	1.49	1.52	1.53
pH (1% Solution)	11.5	X	X
Viscosity @ 25°C	X	290 cps	X