





SODA SOLVAY® LIGHT

SODA SOLVAY® LIGHT

Light Soda Ash

Origin	Europe
Chemical name: Sodium carbonate / Soda ash	
CAS – N°	497-19-8
EINECS – N°	207-838-8
EC – N°	011-005-00-2
CLP Classification: H319	Causes serious eye irritation
Chemical formula	Na ₂ CO ₃
Molecular weight	106
Physical properties	
Appearance: White powder	
Density in kg/dm ³	2,533
Melting point °C	851
Solubility in water at 20°C in g/1000g	214
pH (1% in water)	11,26

Product Data Sheet



➤ Applications

Glass Industry – Raw Material for melting

Chemical Industry – Production of sodium derivatives

Detergents – Alkaline support

Metallurgical processes – Desulfurization of pig iron – Raw material for melting, ...

Flue gas treatment – Removal of acidic components

➤ Transport / Packaging

Bulk: wagon, truck, ship

Packaging: plastic bags, bulk bags

Some applications of this product may be regulated or restricted by national or international standards (e.g. food additives, feeding stuff, water treatment, the cosmetic or pharmaceutical industry, etc). The buyer and eventual user, in his sole and entire liability, shall respect those standards, orders of any relevant authority, and all existing patents and intellectual properties rights; and shall comply with the laws and the regulations applicable to our products and/or to his activity. The buyer and the eventual user must independently determine the suitability of this product for any particular purpose and its manner of use.

SOLVAY CHEMICALS INTERNATIONAL
Rue du Prince Albert, 44
B-1050 Brussels

Internet: <http://www.solvay.com>

Specification	SPE – C 05.19.10		
Date	01/2011	Ed./ Issue	01
Replace			



Typical analytical values

	Europe
Chemical analysis	
Na_2CO_3 (Na_2O) *	99,5 % (58,2 %)
NaCl	0,15 %
Na_2SO_4	0,01 ~ 0,02 %
CaO	32 ~ 60 ppm
MgO	40 ~ 78 ppm
Fe_2O_3	3 ~ 10 ppm
Loss on drying *	0,1 ~ 0,6 %
Free flowing density	0,53 ~ 0,57 kg/dm ³
Granulometry	
> 2 mm	0,2 ~ 1,2 %
> 1 mm	0,5 ~ 2,3 %
> 0,5 mm	12 ~ 40 %
< 0,125 mm	1,6 ~ 3,0 %
< 0,063 mm	0,2 ~ 1,0 %
< 0,063 mm	0,2 ~ 1,0 %

Specification

Chemical analysis	
Na_2CO_3 (Na_2O) *	≥ 98 % (57,3 %)
NaCl	≤ 0,5 %
Na_2SO_4	≤ 0,04 %
CaO	≤ 150 ppm
MgO	≤ 150 ppm
Fe_2O_3	≤ 30 ppm
Loss on drying *	≤ 1,5 %
Free flowing density	≥ 0,48 kg/dm ³ ≤ 0,67 kg/dm ³
(*) Ex works or after drying (2 hrs at 250°C)	
Granulometry	
> 1 mm	≤ 5 %
> 0,25 mm	≤ 25 %
< 0,125 mm	≤ 90%
< 0,063 mm	≤ 60 %

List of analytical methods see: ANA – C 40 00 00 JULY 2000

The information contained in this document is given in good faith and by way of information at the time of printing. As the potential uses of our products are many and outside our control, each user is responsible for asking us for information on planned applications, as we cannot be held liable on the basis of general information. The buyer is required to monitor and respect, in his sole liability, the conditions under which our products are stored and used in his territory, to provide all required information to the user, and to respect all existing patents and all regulations applicable to our products and to his activity.

SOLVAY CHEMICALS INTERNATIONAL
Rue du Prince Albert, 44
B-1050 Brussels

Internet: <http://www.solvay.com>

Specification	SPE – C 05.19.10		
Date	01/2011	Ed./ Issue	01
Replace			

